

GEOLOGY

Limestone

BEST USE

Exterior Walls of Buildings and Fireplaces Stone Shall be Mortared In

WEIGHT CALCULATOR PER SQUARE FOOT OF FLATS AND LINEAL FOOT OF CORNERS

14.9 Lbs Average Per Sf

19.1 Lbs Average Per Lf

QUANTITY PER PALLET/CRATE

Full Bed Veneer: 4,000 Lbs

Thin Veneer: 150 Sf (2,200-2,300 Lbs)
200 (3,000-3,100)



COTTAGE CREAM Rubble

FULL VENEER

Common Coverage		
Standard Joint	Dry Stack	Overgrout
40 Square Feet / Ton	30 Sf / Ton	50 Sf / Ton

DIMENSIONS

Random Sizes:	3"-10"
Thickness:	3"-5"

TYPICAL CHARACTERISTICS

Chopped All Sides
Random Irregular Shapes

STANDARD SIZE TOLERANCE

Thickness:	3"-5.5"
------------	---------

SHIPPING DETAILS: FULL TRUCK QUANTITY

Flatbed:	12-13 Pallets
Dry Van:	12-13 Pallets
Rail Container:	12-13 Pallets

THIN VENEER

Common Coverage	Per Crate	
Standard Joint	Dry Stack	Overgrout
200 Square Feet	180 Sf / Ton	220 Sf / Ton

DIMENSIONS

Random Sizes:	3-10"
Thickness:	1"-1.5"
Corner Returns:	3"-5"

TYPICAL PIECE

Chopped All Sides
Random Irregular Shapes

STANDARD SIZE TOLERANCE

Thickness:	1"-1.5"
------------	---------

SHIPPING DETAILS: FULL TRUCK QUANTITY

Flatbed:	21-22 Pallets / 17-18 Crates
Dry Van:	19-20 Pallets / 15-16 Crates
Rail Container:	18-19 Pallets / 14-15 Crates

ASTM TESTING

Average Dry Weight (g).....	543.6
Average Saturated Weight (g).....	570.7
Average Suspended Weight (g).....	332.5
Average 48-hr Absorption (%).....	5.18
Average Bulk Specific Gravity	2.27
Average Modulus of Rupture (DRY) (psi)	803.5
Average Modulus of Rupture (WET) (psi).....	829.1
Average Compressive Strength (DRY) - Perpendicular (psi).....	3,809.2
Average Compressive Strength (DRY) - Parallel (psi)	7,332.2
Average Compressive Strength (WET) - Perpendicular (psi).....	2,473.4
Average Compressive Strength (WET) - Parallel (psi).....	3,776.8